

ThixoSUM2



ThixoSUM2 is specifically engineered to provide outstanding results in the most extreme conditions. The incredible flexibility in performance allows the grease to be used in both high and low speed operation and is the ideal application for centralized lube systems. Operates efficiently under extreme loads and pressures.

ThixoSUM2 uses an advanced thickening agent (Overbased Calcium Sulfonate) and superior additive technology which exhibits a water resistance in excess of 20 times that of conventional grease thickeners.

ThixoSUM2: For use in centralized greasing systems and as a multipurpose high-performance grease to provide protection over a broad range of conditions.

ThixoSUM2 demonstrates outstanding sheet stability, and exhibits a broad temperature range dependent on application requirements.

Proven to deliver performance in mining, industrial manufacturing, marine, agriculture, forestry, and construction industries.

NLGI GC-LB

Product ID#	3420-425-30 (425g Tube x 30)	3400-17-1 (17kg Pail)	3400-55-1 (55kg Keg) 3400-180-2 (180kg Drum)
--------------------	-------------------------------------	------------------------------	---

<u>TYPICAL PROPERTIES</u>	<u>ASTM METHOD</u>	<u>ThixoSUM2</u>
NLGI Consistency Grade		2
Appearance		Brown, Smooth, Buttery
Worked Penetration (60 Strokes - mm/10)	D 217	288
Dropping Point (°C)	D 2265	>308°C (586°F)
Oil Separation (% W loss)	D 1742	0.0
<u>BASE OIL PROPERTIES</u>		
Viscosity @ 40°C (cSt)	D 445	130 -145
Viscosity @ 100°C (cSt)	D 445	13.6
<u>PERFORMANCE TESTING</u>		
Timken OK load (kg)	D 2509	>36 (80 lbs)
Load Wear Index - 60min (kgf)	D 2596	88.9
Weld Load (kg)	D 2596	500
4 Ball Wear (mm)	D 2266	0.48
Water Washout (% loss @ 79°C (175°F))	D 1264	1.28
Salt Spray Corrosion Test, 5% Salt Fog @ 300hrs	D 610 + B117	#10 No Corrosion
Low Temperature Torque (N-m @ -20°C) 1hr running	D 4693	0.03
Corrosion Prevention	D 1743	Pass

GREASE COMPATIBILITY											
	Thickener	1	2	3	4	5	6	7	8	9	10
1	Ca sulfonate complete		NC	NC	FC	FC	NC	FC	FC	NC	NC
2	Aluminum complex	NC		NC	FC	NC	NC	NC	NC	NC	NC
3	Barium	NC	NC		FC	NC	NC	NC	NC	NC	NC
4	Anhydrous calcium	FC	FC	FC		SC	FC	FC	FC	NC	NC
5	Calcium complex	FC	NC	NC	SC		NC	NC	FC	FC	NC
6	Clay	NC	NC	NC	FC	NC		NC	NC	NC	NC
7	Lithium	FC	NC	NC	FC	NC	NC		FC	NC	SC
8	Lithium complex	FC	NC	NC	FC	FC	NC	FC		NC	SC
9	Polyurea	NC	NC	NC	NC	FC	NC	NC	NC		NC
10	Sodium	NC	NC	NC	NC	NC	NC	SC	SC	NC	

Legend:

FC - Fully compatible

SC - Somewhat compatible: Mixture soften, but remains grease like

NC - Not compatible: Mixtures soften severely and do not remain grease like

All precautions were taken to ensure that the data in this table are correct, however it is recommended that you consult the manufacturer before mixing two different products.